

Blasting Grit

P/N 44.01.027

Applications

- Field of application
- Blasting systems

Mineral abrasive for gentle cleaning, deburring, smoothing, roughness reduction, matting, surface finishing and hardening
 Pressure blasting systems, injector blasting systems

Typical Physical Properties

- Hardness according to Mohs
- Grain shape
- Melting point
- Specific weight
- Bulk density depending on grain size
- Average grain size

Approx. 6
 Round
 Approx. +1,400 °C
 Approx. 2.5 g/cm³
 Approx. 1.5 g/cm³
 100 µm to 200 µm

Chemical Average Analysis

- SiO₂
- Na₂O
- CaO
- MgO
- Al₂O₃
- Fe₂O₃
- Other ingredients

Min. 65.0 %
 Min. 14.0 %
 Min. 8.0 %
 Min. 2.5 %
 0.5 % to 2.0 %
 Max. 0.15 %
 Max. 2.0 %

Further Information

- Packaging

Plastic container 1 kg (2.2 lbs)

